



Europäisches Patentamt
European Patent Office
Office européen des brevets



Publication number: **0 513 545 A2**

12

EUROPEAN PATENT APPLICATION

21 Application number: **92106607.2**

51 Int. Cl.⁵: **C08G 69/44**

22 Date of filing: **16.04.92**

30 Priority: **19.04.91 US 687801**

43 Date of publication of application:
19.11.92 Bulletin 92/47

84 Designated Contracting States:
DE FR GB NL

71 Applicant: **HOECHST CELANESE
CORPORATION**
Route 202-206 North
Somerville, N.J. 08876(US)

72 Inventor: **Cherylyn, Lee**
384 Penns Way
Basking Ridge, New Jersey(US)
Inventor: **Larry, F. Charbonneau**
64 Mountainside Road
Mendham, New Jersey(US)

74 Representative: **von Kreisler, Alek et al**
Patentanwälte von Kreisler Selting Werner
Deichmannhaus am Hauptbahnhof
W-5000 Köln 1(DE)

54 Melt processable poly(ester-amide) capable of forming an anisotropic melt.

57 A melt processable poly(ester-amide) which is capable of forming an anisotropic melt phase is provided. A poly(ester-amide) of the present invention may have recurring units of: (a) 4-hydroxybenzoyl moiety, (b) 6-oxy-2-naphthoyl moiety, (c) 4,4'-biphenol moiety, (d) terephthaloyl moiety, and (e) an aromatic moiety capable of forming an amide linkage in the proportions indicated. Preferably, the moiety capable of forming an amide linkage is derived from p-aminophenol, p-phenylenediamine, N-acetyl-p-aminophenol, etc. The resulting poly(ester-amide) is capable of undergoing melt-processing in the temperature range of from about 300° to about 400° C.

EP 0 513 545 A2

BEST AVAILABLE COPY

TECHNICAL FIELD

The present invention relates generally to high performance liquid-crystal polyester resins and more specifically to a melt-processable polyester-amide capable of forming an anisotropic melt derived from 4-oxybenzoyl, 6-oxy-2-naphthoyl, terephthaloyl, biphenol and an aromatic moiety capable of forming an amide linkage.

BACKGROUND OF THE INVENTION

Liquid crystalline or thermotropic polyesters capable of forming an anisotropic melt are known high performance materials useful for manufacturing films, fibers, molded articles and like items. While these materials typically exhibit superior temperature resistance and mechanical properties as compared to commodity resins, they are often times difficult to synthesize and melt-process due to a tendency to become intractable if the composition is not carefully controlled, or alternatively, desirable properties as aforementioned can be lacking if the ratio and/or selection of components is not within critical ranges.

Various attempts have been made to improve the processability and/or mechanical properties of liquid crystalline polyesters, including by the incorporation of amide linkages into such polymers.

U.S. Patent No. 4,282,842 discloses poly(ester-amides) prepared from an aromatic dicarboxylic acid, ethylene glycol, and a p-acylaminobenzoic acid. A similar disclosure is Japanese Publication 54-125271. European Patent Application No. 79301276.6 (Publication No. 0 007 715) discloses melt processable fiber-forming poly(ester-amides) comprising residues of one or more aminophenols selected from p-aminophenol and p-N-methylaminophenol and residues of one or more dicarboxylic acids. The poly(ester-amide) disclosed contains a balance of linear difunctional residues and dissymmetric difunctional residues derived from either the aminophenols or their acids. The linear difunctional residues and dissymmetric difunctional residues are chosen so as to give a product which melts below its decomposition temperature and exhibits optical anisotropy in the melt.

U.S. Patent No. 3,859,251 discloses a poly(ester-amide) which comprises 50 to 100 mole percent of the moiety derived from an acyclic aliphatic dicarboxylic acid.

U.S. Patent No. 3,809,679 discloses poly(ester-amides) consisting of 10 to 90 mole percent of recurring structural units derived from a dicarboxylic acid dihalide and a dihydroxy compound of a specified formula and 10 to 90 mole percent of recurring structural units derived from a dicarboxylic acid dihalide and a diamino compound of a specified formula. The poly(ester-amides) described specifically exclude moieties derived from aromatic hydroxyacids, such as the 6-oxy-2-naphthoyl moiety included in the poly(ester-amide) of the present invention.

Commonly assigned U.S. Patent No. 4,330,457, incorporated herein by reference, discloses melt processable poly(ester-amides) capable of forming an anisotropic melt phase derived from 6-hydroxy-2-naphthoic acid, dicarboxylic acid, and aromatic monomer capable of forming an amide linkage. The resulting poly(ester-amide) exhibits a melting temperature below approximately 400° C.

Other poly(ester-amides) are disclosed and claimed in U. S. Patent Nos. 4,966,956; 4,355,132 and 4,339,375. The '956 patent teaches a four-component poly(ester-amide) including 4-oxybenzoyl, biphenol, an amide-forming monomer and either terephthaloyl or isophthaloyl moieties.

Commonly assigned U.S. Patent No. 4,473,682, incorporated herein by reference, discloses melt processable polyesters capable of forming an anisotropic melt comprising a relatively low concentration of 6-oxy-2-naphthoyl moiety, 4-oxybenzoyl moiety, 4,4'-dioxybiphenyl moiety, and terephthaloyl moiety. This polyester forms an atypical highly tractable anisotropic melt phase.

Commonly assigned U.S. Patent No. 4,351,917, incorporated herein by reference, discloses a melt processable poly(ester-amide) which is capable of forming an anisotropic melt phase derived from 6-hydroxy-2-naphthoic acid, an aromatic moiety capable of forming an amide linkage, and optionally, other aromatic moieties derived from aromatic hydroxyacid.

Commonly assigned U.S. Patent No. 4,351,918, incorporated herein by reference, shows a melt processable poly(ester-amide) which is capable of forming an anisotropic melt phase derived from 6-hydroxy-2-naphthoic acid, other aromatic hydroxyacid, carbocyclic dicarboxylic acid, and aromatic monomers capable of forming an amide linkage.


55 SUMMARY OF THE INVENTION

It has been found that compositions in accordance with the present invention have a unique combination of temperature resistance, mechanical properties and processability at relatively low temperature.

A melt processable poly(ester-amide) capable of forming an anisotropic melt phase at a temperature below approximately 400° C is provided. The poly(ester-amide) of the present invention contains recurring moieties I, II, III, IV, and V wherein:

I is


5



10

II is


15



20

III is


25



30

IV is

35



40


wherein Ar is a divalent moiety containing at least one aromatic ring; Y & Z are divalent organic or inorganic radicals and may be the same or different and include at least one member selected from the group consisting of NH or NR where R is a 1-6 carbon containing alkyl moiety or an aryl moiety; and V is the residue of an aromatic dioyl precursor.

Generally speaking, the poly(ester-amide) of the present invention contains from about 1 to about 15 mole percent of moiety I, from about 20 to about 70 mole percent moiety II, from about 5 to about 40 mole percent of moiety III, from about 1 to about 20 mole percent of moiety IV, and from about 5 to about 40 mole percent of moiety V.

Typically, the compositions contain from about 2.5 to about 10 mole percent moiety I, 20 to 70 mole percent moiety II, 5 to 25 mole percent moiety III, 2.5 to 15 percent moiety IV, and 2.5 to 15 percent of moiety V. A preferred composition contains about 2.5 to 7.5 mole percent moiety I, at least 50 mole percent of moiety II, from about 5 to about 20 percent of moiety III, from about 2.5 to 10 mole percent of moiety IV, and about 15 to 25 mole percent of moiety V.

A preferred moiety IV is

55



5 derived from p-aminophenol or N-acetyl-p-aminophenol.

Moiety V is most preferably a terephthaloyl moiety but may be selected from the group consisting of isophthaloyl, terephthaloyl or mixtures thereof.

10 The melt-processable poly(ester-amide) according to the invention is capable of forming an anisotropic melt phase below about 350 °C. and is capable of undergoing melt-processing in the temperature range of from about 300 °C to about 400 °C. A melt processable poly(ester-amide) according to the invention may exhibit an inherent viscosity in the range of about 1.0 to 12.0 dl/g when dissolved in a concentration of 0.1 percent by weight in pentafluorophenol at 60 °C and may exhibit a melt viscosity in the range of from about 15 50 to 1500 poise at a shear rate of 10^3 sec^{-1} measured at 365 °C in a capillary rheometer.

The compositions according to the invention are useful for making shaped articles such as fibers and molded articles as will become apparent from the examples hereinafter provided.

DETAILED DESCRIPTION

20 The poly(ester-amide) of the present invention includes five recurring moieties which when combined in the poly(ester-amide) have been found to form an atypical highly tractable anisotropic melt phase at a temperature below approximately 400 °C., and preferably below approximately 370 °C. (e.g., approximately 350 °C. in a particularly preferred embodiment). The poly(ester-amide) melt endotherm (T_m) may be 25 confirmed by the use of a differential scanning calorimeter (DSC) employing repeat scans at a 20 °C. per minute heat-up rate and observing the peak of the DSC melt transition. The poly(ester-amide) of the present invention may be considered crystalline in the sense that fibers melt extruded therefrom exhibit X-ray diffraction patterns using Ni-filtered $\text{CuK}\alpha$ radiation and flat plate cameras characteristic of polymeric crystalline materials. Because of its ability also to exhibit anisotropic properties (i.e., liquid crystalline 30 properties) in the melt, the poly(ester-amide) readily can form a product having a highly oriented molecular structure upon melt processing. Such product has been found to exhibit unusually high tenacity and modulus. Preferred poly(ester-amides) are capable of undergoing melt processing at a temperature in the range of approximately 320 °C. to 390 °C. (e.g., at approximately 345 °C. to 360 °C.).

As will be readily appreciated by those skilled in the art, the present invention is in no way limited by 35 the examples which follow. Although the invention is illustrated specifically with N-acetyl-p-aminophenol providing an amide linkage, such linkages could be derived from p-aminophenol, p-N-methylaminophenol, p-phenylenediamine, N-methyl-p-phenylenediamine, N,N'-dimethyl-p-phenylenediamine, m-aminophenol, 3-methyl-4-aminophenol, 2-chloro-4-aminophenol, 4-amino-1-naphthol, 4-amino-4'-hydroxydiphenyl, 4-amino-4'-hydroxydiphenyl ether, 4-amino-4'-hydroxydiphenyl methane, 4-amino-4'-hydroxydiphenyl ethane, 4- 40 amino-4'-hydroxydiphenyl sulfone, 4-amino-4'-hydroxydiphenyl sulfide, 4,4'-diaminophenyl sulfide (thiodianiline), 4,4'-diaminodiphenyl sulfone, 2,5-diaminotoluene, 4,4'-ethylepedianiline, or 4,4'-diaminodiphenoxyethane, as well as 3,4'-diaminophenyl X, 3-amino-4'-hydroxyphenyl X, and 3-hydroxy-4'-aminodiphenyl X, wherein X is selected from the group consisting of sulfide, sulfone, ether and methane.

The poly(ester-amide) of the present invention may optionally incorporate approximately 1 to 50 percent 45 by weight (preferably approximately 10 to 30 percent by weight), based upon the total weight of the polymers, of a solid filler and/or reinforcing agent when making a molded article. Representative filler materials include calcium silicate, silica, clays, talc, mica, polytetrafluoroethylene, graphite, alumina trihydrate, sodium aluminum carbonate, barium ferrite, wollastonite, etc. Representative reinforcing fibers include glass fibers, graphitic carbon fibers, amorphous carbon fibers, synthetic polymeric fibers, alumina 50 fibers, aluminum silicate fibers, aluminum oxide fibers, titanium fibers, magnesium fibers, rock wool fibers, steel fibers, tungsten fibers, or wollastonite fibers having an aspect ratio greater than 3 to 1.

EXAMPLE I

55 This example illustrates the preparation of a poly(ester-amide) from a 6 mole reaction mixture of 4-hydroxybenzoic acid ("HBA"), 6-hydroxy-2-naphthoic acid ("HNA"), 4,4'-biphenol ("BP"), terephthalic acid ("TA"), and N-acetyl-p-aminophenol ("APAP") in the ratio 60.0:5.0:12.5:17.5:5.0 (5.0 mole % HNA and 5.0 mole % APAP).

To a 2 litre "Slim Jim" flask equipped with a C-shaped 316 stainless steel, gas inlet tube, thermocouple, a Vigreux column attached to a condenser and receiver were added the following:

- (a) 496.8 grams of 4-hydroxybenzoic acid (3.6 moles);
- (b) 56.4 grams of 6-hydroxy-2-naphthoic acid (0.3 moles);
- 5 (c) 139.5 grams of 4,4'-biphenol (0.75 moles);
- (d) 174.3 grams of terephthalic acid (1.05 moles);
- (e) 45.3 grams of N-acetyl-p-aminophenol (0.3 moles); the flask was immersed in a sand bath and provided with means to accurately control the temperature. The flask was thoroughly purged of oxygen by evacuation and flushed with nitrogen three times, and slowly heated in the sand bath; and
- 10 (f) 10 mls. of a 1.2% (w/v) solution of potassium acetate in acetic acid (60 ppm K^+) were added as a catalyst along with 598.8 grams of acetic anhydride (2.5 % excess). Acetic acid began to distill over and was collected in a graduated cylinder.

The contents of the flask were heated while stirring at a rate of 75 rpm (torque = 13 mV) to 152°C. over a period of 111 minutes at which time 100 mls. of acetic acid had been collected. The polymerization
15 temperature was then gradually raised to 350°C. over a period of 215 minutes at which time a total of 660 mls. of acetic acid had been collected. The flask was evacuated to a pressure of less than 1.0 mm at 350°C. while stirring. The polymer was stirred at 350°C. until the desired Δ torque was achieved (i.e., Δ torque = 50 mV for this example). During this period the polymer melt continued to increase in viscosity while the remaining acetic acid was removed from the flask.

20 The resulting poly(ester-amide) had an inherent viscosity (I.V.) of 9.1 dl/g as determined in a pentafluorophenol solution of 0.1 percent by weight concentration at 60°C., and a melt viscosity (M.V.) of 581 poise at a shear rate of 10^3 sec^{-1} measured at 345°C in a capillary rheometer using an orifice of 0.015 inch diameter and 1.0" length.

25 I.V. = $\ln(\eta_{\text{rel}})/c$

where c = concentration of solution (0.1 percent by weight), and η_{rel} = relative viscosity. The relative viscosity was measured by dividing the flow time in a capillary viscometer of the polymer solution by the flow time for the pure solvent. When the polymer was subject to differential scanning calorimetry
30 (20°C./min. heating rate), it exhibited a melt endotherm (T_m) peak at 343°C. The polymer melt was optically anisotropic.

EXAMPLE II - X

35 In accordance with the foregoing example I, nine additional compositions were prepared having different proportions of the five ingredients noted hereinabove. Composition, melting point, I.V. and M.V. for the inventive compositions appear in Table I below. Unless otherwise indicated, properties were measured as in Example I.

40

45

50

55

TABLE I

COMPOSITION MELTING POINT, I.V. AND M.V. OF EXAMPLES I - X COMPOSITION (MOLE PERCENT)				
EXAMPLE	HBA:HNA:BP:TA:APAP	T _m , °C	I.V. dl/g	M.V. POISE
I	60:5.0:12.5:17.5:5.0	343	9.1	581*
II	60:5.0:15:17.5:2.5	343	9.5	538*
III	60:5.0:10.0:17.5:7.5	362	7.8	1015*
IV	60:3.5:15.75:18.25:2.5	363	8.5	428**
V	60:3.5:13.25:18.25:5.0	359	9.0	365**
VI	60:3.5:11.75:18.25:6.5	357	7.1	960**
VII	60:3.5:10.75:18.25:7.5	370	7.3	686**
VIII	50.0:15.0:7.5:17.5:10.0	323	9.1	976**
IX	40:15.0:17.5:22.5:5.0	260	8.8	878**
X	30:15.0:22.5:27.5:5.0	327	8.5	567**

* measured at 345 °C;

** measured at 340 °C;

* measured at 360 °C

** measured at 365 °C

COMPARATIVE EXAMPLE A

This example illustrates the preparation of a polyester from a 7 mole reaction mixture of 4-hydroxybenzoic acid, 6-hydroxy-2-naphthoic acid, 4,4'-biphenol, and terephthalic acid in the ratio 60.0:3.5:18.25:18.25 (3.5 mole % HNA and 0.0 mole % APAP). The procedure of Example I was substantially repeated with the exception that the following components were charged into the flask:

(a) 579.6 grams of 4-hydroxybenzoic acid (4.2 moles);

(b) 46.1 grams of 6-hydroxy-2-naphthoic acid (0.24 moles);

(c) 237.6 grams of 4,4'-biphenol (1.28 moles);

(d) 212.1 grams of terephthalic acid (1.28 moles); and

(e) 10 mls. of a 1.2% (w/v) solution of potassium acetate in acetic acid (60 ppm K⁺) were added as a catalyst along with 598.8 grams of acetic anhydride (2.5 % excess); the desired Δ torque was 50 mV, and the reaction temperature was 355 °C.

The resulting wholly aromatic polymer had an I.V. of 9.2 dl/g as determined in pentafluorophenol at 60 °C., and an M.V. of 492 poise at a shear rate of 10³ sec⁻¹ measured at 365 °C in a capillary rheometer. When the polymer was subjected to DSC, it exhibited a T_m of 376 °C.

COMPARATIVE EXAMPLE B

This example illustrates the preparation of a poly(ester amide) from a 6 mol reaction mixture of 4-hydroxybenzoic acid, isophthalic acid, terephthalic acid, 4,4'-biphenol, and N-acetyl-p-aminophenol in the ratio of 50.0:12.5:12.5:20.0:5.0.

The following components were charged into the flask:

a) 3.0 mole (414.0 g) 4-hydroxybenzoic acid;

b) 0.75 mole (124.5 g) isophthalic acid;

c) 0.75 mole (124.5 g) terephthalic acid;

d) 1.2 mole (223.2 g) 4,4'-biphenol;

e) 0.3 mole (45.3 g) N-acetyl-p-aminophenol; and

f) 10 ml of a 1.2 (w/v) solution of potassium acetate in acetic acid (60 ppm K⁺) were added as a catalyst along with 600 ml acetic anhydride (2.5% excess) and heated to 350 °C. The resulting wholly aromatic polymer had an I.V. of 3.6 dl/g as determined in

pentafluorophenol at 60°C, and an M.V. in the range of about 500-700 poise at a shear rate of 10^3 sec^{-1} measured at 340°C in a capillary rheometer. When the polymer was subject to DSC, it exhibited a T_m of 281°C.

5 FIBER PROPERTIES

Fibers were prepared from the compositions of Examples IV, V, and Comparative Example A. The fibers were heat-treated for eight hours in a nitrogen atmosphere at 300°C in an oven. Tenacity, elongation and modulus were defined in accordance with ASTM D 3822-90 and reported in Table II, below, along with corresponding data for Comparative Example B wherein the heat treatment was in stepwise fashion, 2 hours at 230°C, followed by 16 hours at 270°C. Examples IV, V, A are approximately 5 denier. The polymer of Example B was difficult to spin; unable to achieve 5 denier fiber, but 8.5 denier fiber was made.

TABLE II

FIBER PROPERTIES AFTER HEAT TREATMENT*			
POLYMER OF EXAMPLE	TENACITY g/d	MODULUS g/d	ELONGATION %
IV	29.2	1040	2.5
V	31.9	1060	2.7
A	21-22	910	2.2-2.3
B	16	475	3.0

* Single Filament


As may be seen from Table II, compositions in accordance with the present invention exhibit both higher modulus and tenacity than other liquid crystalline polymers. This surprising and highly useful characteristic makes such compounds particularly suitable for high performance applications.

While the present invention has been described hereinabove in connection with numerous examples, various modifications will be apparent to those of skill in the art. Such modifications are within the spirit and scope of the present invention, which is limited and defined only by the appended claims.


35 Claims

1. A melt processable poly(ester-amide) capable of forming an anisotropic melt phase at a temperature below about 400°C. having recurring moieties I, II, III, IV and V wherein:


I is




II is



III is




IV is



wherein Ar is a divalent moiety containing at least one aromatic ring, Y and Z are divalent organic or inorganic radicals and may be the same or different and include at least one member selected from the group consisting of NH or NR where R is a 1-6 carbon containing alkyl moiety or an aryl moiety; and V is the residue of an aromatic dioyl precursor; and wherein said poly(ester-amide) contains from about 1 to about 15 mole per cent of moiety I, from about 20 to about 70 mole percent moiety II, from about 5 to about 40 mole percent of moiety III, from about 1 to about 20 mole per cent of moiety IV, and from about 5 to about 40 mole per cent of moiety V.

2. The poly(ester-amide) according to claim 1 wherein moiety IV is



3. The poly(ester-amide) according to claim 2 wherein moiety IV is derived from p-aminophenol or N-acetyl-p-aminophenol.

4. The polyester according to claim 3 wherein moiety IV is derived from N-acetyl-p-aminophenol.

5. The poly(ester-amide) according to claim 1, wherein moiety V is a terephthaloyl moiety.

6. The poly(ester-amide) according to claim 1 wherein moiety V is selected from the group consisting of isophthaloyl, terephthaloyl or mixtures thereof.

7. The melt-processable poly(ester-amide) according to claim 1 which is capable of forming an anisotropic melt phase at a temperature of about 350 °C.

8. The melt-processable poly(ester-amide) according to claim 1 which is capable of undergoing melt-processing in the temperature range of from about 300 °C. to about 400 °C.

9. A melt-processable poly(ester-amide) according to claim 1 wherein the aromatic rings of moieties I, II, III, IV, and V are substantially free of ring substitution.

10. A fiber which has been melt spun from the poly(ester-amide) according to claim 1.

11. An injection molded article comprising the melt processable poly(ester-amide) according to claim 1.

12. A shaped article consisting essentially of the poly(ester-amide) according to claim 1.


13. A melt processable poly (ester-amide) according to claim 1 which exhibits an inherent viscosity in the range of about 1.0 to 12.0 dl/g when dissolved in a concentration of 0.1 percent by weight in

pentafluorophenol at 60° C.


14. A melt processable poly(ester-amide) according to claim 1 which exhibits a melt viscosity in the range of from about 50 to 1500 poise at a shear rate of 10^3 sec^{-1} measured at 365° C in a capillary rheometer.

15. A melt processable poly(ester-amide) capable of forming an anisotropic melt phase at a temperature below approximately 400° C consisting essentially of recurring moieties I, II, III, IV and V wherein:


I is




II is



III is



IV is



wherein Ar is a divalent moiety containing at least one aromatic ring, Y & Z are divalent organic or inorganic radicals and may be the same or different and include at least one member selected from the group consisting of NH or NR where R is a 1-6 carbon containing alkyl moiety or an aryl moiety; and

V is the residue of an aromatic di-oyl precursor or mixtures of terephthaloyl with other aromatic di-oyls; and wherein moiety I is present in amounts of from about 2.5 to about 10 mole per cent, moiety II is present in amounts from about 20 to about 70 mole per cent, moiety III is present in amounts of from about 5 to about 25 mole per cent, moiety IV is present in amounts of from about 2.5 to about 15 mole per cent, and moiety V is present in amounts of from about 10 to about 25 mole per cent.

16. The melt-processable poly(ester-amide) according to claim 15, wherein moiety V consists of tereph-

thaloyl.

17. The melt-processable poly(ester-amide) according to claim 15, wherein moiety IV is derived from N-acetyl-p-aminophenol.

5

18. The melt processable poly(ester-amide) according to claim 15 wherein moiety I is present in an amount of from about 2.5 to about 7.5 mole per cent, moiety II is present in an amount of at least about 50 mole per cent, moiety III is present from about 5 to about 20 per cent, moiety IV is present in an amount of from about 2.5 to about 10 mole per cent, and moiety V is present from about 15 to about 25 mole per cent.

10

19. A fiber spun from the composition of claim 15.

20. A shaped article formed from the composition of claim 15.

15

20

25

30

35

40

45

50

55

**This Page is Inserted by IFW Indexing and Scanning
Operations and is not part of the Official Record**

BEST AVAILABLE IMAGES

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ BLACK BORDERS
- ☐ IMAGE CUT OFF AT TOP, BOTTOM OR SIDES
- ☒ FADED TEXT OR DRAWING
- ☐ BLURRED OR ILLEGIBLE TEXT OR DRAWING
- ☐ SKEWED/SLANTED IMAGES
- ☐ COLOR OR BLACK AND WHITE PHOTOGRAPHS
- ☐ GRAY SCALE DOCUMENTS
- ☐ LINES OR MARKS ON ORIGINAL DOCUMENT
- ☐ REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY
- ☐ OTHER: _____

IMAGES ARE BEST AVAILABLE COPY.

As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.